



# A. S. RUBBER

Bohra Mills Compound, Main Bazar, Ballabgarh - 121004

Phone: +91-0129-4062692; Fax: +91-0129-4062695

## Material Test Report

Customer	M/s Gadli Industries:	Bill No.	73			
Part No.	AS 7044, AS 2787	Despatch Date.	18.08.2015			
Part Name	EPDM Rubber Gasket					
S.No.	Characteristics	UOM	Test method	Specification	Observation	Status
1	Material	---	ASTM D - 297	EPDM	EPDM	OK
2	Hardness	Shore A	ASTM D - 2240	65±5	68	OK
3	Tensile strength	Kgf / cm <sup>2</sup>	ASTM D - 412	60 MIN	63	OK
4	Elongation @ break	%	ASTM D - 412	200 MIN	235	OK
5	Compression set @ 70°C / 22 hrs.	%	ASTM D - 395	50 MAX	41	OK
6	Ozone Resistance @ 50pphm / 40°C / 20 % Strain / 72 hrs.	---	ASTM D - 1149	NO CRACK	No crack observed	OK

FOR A. S. RUBBER

  
Auth. Signatory

Remarks : 1) The company does not take Liability to comply with any other test result except for the once mentioned in the product drawing, even though it may be part of this report.